



ImageLOC® Technical Specifications

PRODUCT DESCRIPTION: ImageLOC® is a proprietary sign printing technology developed by Gopher Sign Company for printing durable, photo quality outdoor or indoor signs. The process begins by coating high quality, heat-treated aluminum alloy sheeting with a proprietary organic material under controlled conditions. This coating is fused to the aluminum and becomes the substrate upon which we apply our inks, eliminating paper, vinyl or plastic from the printing process. Once imaging is completed, a proprietary organic top coat is applied, fused and bonded with the ink and substrate, sealing the image between the topcoat and substrate. This protects the four-color print from harmful UV rays, water, hail, salt, sand, rain, graffiti and vandalism.

IMAGING: The ImageLOC® printing process is done on a flatbed inkjet printer utilizing inks that have been carefully tuned to the process. Utilizing input resolutions ranging between 200 and 300 dpi, the output resolution is printed at 1200 dpi, providing accurate, bright and vibrant reproduction of photographic images. This technology is also well-suited to reproducing small text and fine detail with amazing accuracy. All images are created in CMYK color space.

ATTRIBUTES: ImageLOC® sign printing technology produces a highly durable sign with the following attributes under normal conditions:

- Lowest cost of ownership of all durable 4-color sign technologies
- Bright, vibrant graphics
- Self-supporting in most common sign sizes
- Extremely durable
- Substantially lighter than other durable sign technologies
- Will not corrode if vandalized
- Graffiti cleans off easily with available cleaners
- Scratch resistant
- Superb UV protection (10-year warranty)
- Impervious to weather
- Excellent impact resistance
- Vandal resistant
- Will not delaminate, blister crack or peel
- Available in .125" thick
- Available in contoured shapes, with or without mounting holes or stainless steel studs, and tamper-proof hardware on the reverse side of the sign
- Printable on one or both sides of the sign

Continued on next page

ImageLOC® Technical Specifications (Continued)

SIGN APPLICATIONS: ImageLOC® printing technology is designed to produce durable photo-quality color images on ImageLOC® signs in outdoor applications that are intended to last for ten years or more. This highly durable sign printing technology is ideal for signs in remote, unattended areas, as well as high-traffic areas, due to its hydrophobic, graffiti-and vandal-resistant finish. It performs well in all climate conditions including sunny locations, shady humid areas, extreme mountain conditions, seashore areas, and/or arid desert locations.

Applications for these signs include:

- Wayfinding signs (parks, trails, campuses, business parks, malls, etc.)
- Interpretive signs and displays
- Exhibit signs, displays and murals
- Regulatory signs
- Corporate identity signage
- Museum signage
- Zoos and aquariums
- Retail signage (restaurants, bars, retail stores, etc.)
- Parking lot and garage signage
- Resort, theme park and recreational facility signage
- Architectural signage
- Monument signs (city welcome signs, park entrance, sub-divisions, industrial parks, etc.)
- Institutional signage (universities, government facilities, hospitals, etc.)
- Gas station/convenience store signage

STANDARD PANEL THICKNESS: ImageLOC® printing technology is used on three different configurations of signs one standard thickness as indicated below:

RIGID SIGNS: ImageLOC® signs have a standard thickness of .125 inches and are rigid enough to perform well without a backer plate or frame up to 24 x 36 inches on free-standing exhibit bases. If the sign is to be mounted on an exhibit base and is larger than 24 x 36 inches, a frame is recommended. Free-standing, framed ImageLOC® signs can be sized up to 36 x 48 inches without concerns about structural integrity. Vertical surface mountings do not have this restriction.

NOTE: Temperature extremes have been known to cause expansion and contraction of outdoor signs with alternate sign technologies such as HPL, Fiberglass Embedment, Polycarbonate and Porcelain Enamel. ImageLOC® sign panels are heat treated at the factory to significantly reduce and/or prevent expansion, contraction and curling of the signs.

Continued on next page

SIGN PANEL MOUNTING OPTIONS: There are many mounting options available for ImageLOC® sign panels to include:

- Extruded frames – These attractive extruded frames can be powder coated with mitered corners to create an attractive mounting configuration for ImageLOC® sign panels. These frames can then be mounted to any number of exhibit base configurations including upright legs and cantilevered stands.
- Bolt-through – Specify location and size of hole required for mounting the sign panels. The holes will be pre-cut and coated at the factory. Tamper-proof hardware is available if required.
- Z-clip mounting – This mounting configuration includes clips that are screwed to the wall and clips adhered to the back of the sign which interlock to form a secure mounting.
- Stainless steel studs – In those applications where the sign panel is to be mounted to another sign or to a back plate with concealed hardware, stainless steel studs on the back side of the sign are an excellent option. We offer flush mounted, stainless steel studs which are adhered to the backside of the sign panel with an adhesive. Each stud has a plate welded to the stud, creating a large surface on which to secure our bond with the aluminum sign. The studs are available with or without tamper-proof nuts and washers. The specifications on each stud size are indicated in the chart below. Each stud size has been engineered to provide high tensile and shear strength, ensuring that the sign panels are secure once mounted. Please see the chart below to select the appropriate stud size.

STAINLESS STEEL STUD SELECTION CHART

Stud Specification	Lengths available in inches	Plate Diameter/ Thickness	Tensile Strength in lbs./Stud	Shear Strength in lbs./Stud
1/4 x 20	.75, 1.0, 1.5, 1.75, 2.0, 2.5	1.25 x .058	500	650
5/16 x 18	1.5	2.0 x .080	1200	1500
3/8 x 16	2.0	2.0 x .080	1200	1500

NOTE: Stud material is Type 304 Stainless Steel

TAMPER PROOF NUTS AND WASHERS

Size	Width (inches)	Diagonal Width (inches)	Height (inches)
1/4 x 20	1.05	1.28	.23
5/16 x 18	1.05	1.28	.23
3/8 x 16	1.05	1.28	.23

NOTE: Add washer thickness to nut height dimension to get the exact height required

ImageLOC® Technical Specifications (Continued)

PANEL SIZES: Rectangular signs printed with ImageLOC® technology are available in sizes up to 48" x 120". If the sign is specified as a contoured shape, the maximum width of the sign panel cannot exceed 47½", allowing 1/8 inch on each side for cutting. Murals of any size can be created by tiling ImageLOC® panels together. When creating murals, the graphics will be indexed over the entire surface of the mural.

CONTOURED SHAPES: ImageLOC® signs can be cut to most shapes on our CNC routers. The minimum size router bit we utilize is a 1/8-inch bit. This determines the maximum inside angles we can cut on the sign panels. **NOTE:** It is standard practice to put a minimum radius corner of 1/8 inch on all panels except those that are tiled, to minimize sharp corners. Please specify the radius of the corners on any panels ordered.

ASTM MECHANICAL PERFORMANCE SPECIFICATIONS

Mechanical Properties	ASTM Test	Grading
Scratch resistance	E-18	Exceeds 9H Pencil Test
UV resistance	G115; D7238	Delta E >10.0
Gloss level	D523	35 ±5 gloss units
Abrasion resistance	D4060-10; D968-05	Pass/Fail test
Indentation hardness	N/A	Barcol rating = 56B
Clarity	D1003	Clarity of underlying images
Chemical & stain resistance	D1308	No damage to finish when doing spot test
Fire/flame/smoke resistance	E84	Class A rating
Corrosive weather resistance	D1654; B-117	<5 millimeter creep when exposed to acidic salt spray
Adhesion	D3359	5B classification
Chalking	D4214	No chalking for 10 years
Hydrophobic	N/A	Highly graffiti resistant

STANDARD WEIGHT: ImageLOC® signs vary in weight based on the thickness of the aluminum used in its construction as indicated below:

Sign Type	Thickness	Weight/Sq. Ft.
ImageLOC®	Rigid .125"	1.75 lbs.

Continued on next page

ImageLOC® Technical Specifications (Continued)

SIGN FINISH: Outdoor signage is generally subject to exposure to bright daylight conditions which can cause glare and compromise the ability to read the sign. For this reason, we have designed ImageLOC® signs with a gloss level that provides optimal clarity and sign visibility in conditions ranging from bright sunshine to shade.

CLEANING: When removing pine sap, dampen a soft cloth with mineral spirits, denatured alcohol or isopropyl alcohol and gently rub the surface until the sap is gone. Gopher Sign's Graffiti-ZAP™ works best at dissolving the sap without damaging the surface. After removing sap from the sign's surface, or anytime the ImageLOC® signs are cleaned, use mild soap and water to remove oily films, dirt, dust, road film and other naturally occurring contaminants from the finish. Do not use abrasive cleaners or acids on the surface as it may damage the finish. See full ImageLOC® cleaning instructions tech sheet for more detailed information.

GRAFFITI REMOVAL: General rule-of-thumb - Faster is easier. Cleaning graffiti (especially paints) off ImageLOC® signs is much easier if you get to it within 24 to 48 hours. Crayon, permanent markers, inks and paints can generally be removed from ImageLOC® signs easily using our Graffiti-ZAP™ organic graffiti remover. Other possible cleaners to try are methyl alcohol, butanol, or isopropyl alcohol. All of these cleaners are mild solvents and can cause skin irritations. We recommend wearing protective gloves such as Nitrile disposable gloves when handling Graffiti-ZAP™ or any of the cleaners referenced above.

CAUTION: Always test graffiti cleaners in a small inconspicuous area to make sure they are compatible and do not damage the surface of the sign. Do not use abrasives or metal brushes on the surface of ImageLOC® signs.